

In the Abstract

Kindly amend the Abstract with the following Abstract marked-up to show the changes that have been made.

The present invention relates to a warp knit having excellent touch and a process of preparing such a warp knit. The present invention provides a warp knit consisting of three plies ~~layers~~, namely a front surface ply ~~layer~~, a rear surface ply ~~layer~~, and an intermediate ply ~~layer~~ arranged between the front surface ply ~~layer~~ and the rear surface ply ~~layer~~, the front surface ply ~~layer~~ consisting of ultra fine yarn with monofilament denier of 0.01 to about 0.3 denier, the intermediate ply ~~layer~~ consist of spandex elastic yarn, the rear surface ply ~~layer~~ consisting of synthetic yarn with monofilament denier of 1 to about 5 denier, wherein the recovery rate of elongation in the directions of wale and course is 25 to about 60 %. The warp knit according to the present invention can be used to manufacture artificial leathers or ladies' clothes.